LARIPUR® LPR 7560

Thermoplastic Polyurethane Elastomer (Polyether)

COIM S.p.A.

Message:

LARIPUR®LPR 7560 is a thermoplastic polyurethane elastomer (polyether) (TPU-polyether) material. This product is available in North America, Latin America or Europe. The processing method is extrusion or injection molding.

LARIPUR® The main features of LPR 7560 are:

Good flexibility

good weather resistance

chemical resistance

Wear-resistant

LARIPUR® Typical application areas of LPR 7560 are: water pipes/pipes/drinking water

| General Information | | | |
|------------------------------|---------------------------------|-------|-------------|
| Features | Flexibility at low temperatures | | |
| | Good wear resistance | | |
| | Good chemical resistance | | |
| | Good weather resistance | | |
| | | | |
| Agency Ratings | NSF 61 | | |
| Forms | Particle | | |
| Processing Method | Extrusion | | |
| | Injection molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.10 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 77 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress | | | ASTM D412 |
| 50% strain | 3.10 | MPa | ASTM D412 |
| 100% strain | 4.40 | MPa | ASTM D412 |
| 300% strain | 12.8 | МРа | ASTM D412 |
| Tensile Strength (Break) | 42.2 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 670 | % | ASTM D412 |
| Tear Strength | 65.0 | kN/m | ASTM D624 |
| Compression Set | | | ASTM D395 |
| 23°C, 70 hr | 22 | % | ASTM D395 |
| 70°C, 22 hr | 50 | % | ASTM D395 |
| Thermal | Nominal Value | Unit | Test Method |
| Vicat Softening Temperature | 70.0 | °C | ASTM D1525 |
| Additional Information | | | |

Abrasion loss, DIN 53516: 35 mm³

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

