## Texalan® 2 Series 265A

Thermoplastic Polyurethane Elastomer (Polyester)

Austin Novel Materials Co. Ltd.

## Message:

Texalan® 2 Series 265A is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) material. It is available in Asia Pacific, Europe, or North America for blow molding, calendering, coextrusion, extrusion, film extrusion, or injection molding.

Important attributes of Texalan® 2 Series 265A are:

Chemical Resistant

High Strength

Impact Resistant

Low Temperature Resistant

Wear Resistant

General Information

300% Strain

Tear Strength

Tensile Stress (Yield)

Tensile Elongation (Break)

Compression Set (70°C)

General Information							
Features	Good Abrasion Resistance						
	High Elasticity High Impact Resistance High Tensile Strength Low Temperature Resistant						
					Oil Resistant		
				Processing Method	Blow Molding		
Calendering							
Coextrusion							
Extrusion							
Film Extrusion							
Injection Molding							
Physical	Nominal Value	Unit	Test Method				
Density	1.08 to 1.12	g/cm³	ISO 1183				
Hardness	Nominal Value	Unit	Test Method				
Shore Hardness (Shore A)	62 to 68		ISO 868				
Mechanical	Nominal Value	Unit	Test Method				
Abrasion Resistance	< 70.0	mm³	ISO 4649				
Elastomers	Nominal Value	Unit	Test Method				
Tensile Stress			ISO 37				
100% Strain	> 1.50	MPa					

MPa

MPa

kN/m

%

%

**ISO 37** 

ISO 37

ISO 34-1

ISO 815

> 3.00

> 18.0

> 850

> 45

< 30

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

