

SEETEC LLDPE UR534

Linear Low Density Polyethylene

Lotte Chemical Corporation

Message:

Broad molding latitude, Excellent stiffness, Good ESCR & Grindability, Butene copolymer

General Information			
Features	Butene Comonomer		
	Good Moldability		
	Good Stiffness		
	High ESCR (Stress Crack Resist.)		
Uses	Containers		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (F50)	> 500	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	13.7	MPa	
Break	24.5	MPa	
Tensile Elongation (Break)	900	%	ASTM D638
Flexural Modulus	490	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	> 590	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -118	°C	ASTM D746
Vicat Softening Temperature	108	°C	ASTM D1525
Melting Temperature	120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

