

Sylvin 8815-70 Grey 9491

Polyvinyl Chloride
Sylvin Technologies Incorporated

Message:

Sylvin 8815-70 Grey 9491 Is A Vinyl Compound Formulated For Extruded Waterstop Applications That Meet The Canadian General Standard 41-GP-35M Type 2.

General Information			
Uses	Building materials		
	Architectural application field		
Agency Ratings	CGSB 41-GP-35M Type 2		
Appearance	Grey		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	70		ASTM D2240
Shaw A, 10 seconds	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	12.4	MPa	ASTM D638
Tensile Elongation (Break)	400	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	48.2	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-54.0	°C	ASTM D746
Melting Temperature	160 - 171	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT