OTECH TPR OTR4595-Sandal

Thermoplastic Elastomer

OTECH Corporation

Message:

FOOTWEAR - SANDAL COMPOUNDS

Applications SANDALS

General Information		
Uses	Footwear	
Physical	Nominal Value	Unit
Specific Gravity	0.948	g/cm³
Hardness	Nominal Value	Unit
Durometer Hardness (10 sec)	45	
Mechanical	Nominal Value	Unit
Tensile Strength	6.89	MPa
Tensile Elongation (Break)	600	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

