

DINALON® B1X25 G30V0-4129

Polyamide 6

Grupo Repol

Message:

DINALON® B1X25 G30V0-4129 is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It is available in Europe.

Characteristics include:

- Flame Rated
- Flame Retardant
- Halogen Free

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
	Halogen Free		
	Low (to None) Phosphorus Content		
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183/A
Humidity ¹	< 0.25	%	ISO 15512/B
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress (Break)	130	MPa	ISO 527-2
Tensile Strain (Break)	2.2	%	ISO 527-2
Flexural Modulus	7600	MPa	ISO 178
Flexural Stress	155	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	45	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	205	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	°C	ISO 306/B
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	V-0	UL 94	
NOTE			
1.	Karl-Fischer		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

