

Novodur® Ultra 4115

Polycarbonate + ABS

Styrolution

Message:

Novodur Ultra 4115 is a PC modified high heat injection molding grade. It provides extraordinary heat resistance combined with high impact strength.

General Information			
Features	High Heat Resistance		
	Ultra High Impact Resistance		
Uses	Automotive Applications		
	Automotive Interior Trim		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
220°C/10.0 kg	6.00	cm ³ /10min	
260°C/5.0 kg	12.0	cm ³ /10min	
Molding Shrinkage	0.60 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	100	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2250	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	47.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield, 23°C	3.8	%	
Break, 23°C	> 15	%	
Flexural Modulus	2200	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	13	kJ/m ²	
23°C	42	kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-30°C	12	kJ/m ²	
23°C	40	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, Annealed	114	°C	ISO 75-2/B
1.8 MPa, Annealed	103	°C	ISO 75-2/A
Vicat Softening Temperature	116	°C	ISO 306/B50
CLTE - Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Relative Permittivity			IEC 60250
100 Hz	3.00		
1 MHz	3.00		
Dissipation Factor			IEC 60250
100 Hz	4.5E-3		
1 MHz	8.5E-3		
Comparative Tracking Index	600	V	IEC 60112
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	230 to 270	°C	
Mold Temperature	70.0	°C	
Injection Velocity	240	mm/sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

