

DynaMix Lite™ 2044-GBD

Polyamide

Polymer Dynamix

Message:

Glass Bead Filled Dimensionally Stable Nylon

Features:

Excellent Processability

Low Density

Good Dimensional Stability

Excellent Chemical Resistance

Applications:

Automotive

Industrial

Small Appliances

General Information			
Filler / Reinforcement	Glass Bead		
Features	Good Chemical Resistance		
	Good Dimensional Stability		
	Good Processability		
	Low Density		
Uses	Appliance Components		
	Appliances		
	Automotive Applications		
	Industrial Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5170	MPa	ASTM D638
Tensile Strength (Yield)	89.6	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	5170	MPa	ASTM D790
Flexural Strength	131	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	93.3 to 110	°C	
Drying Time	3.0 to 5.0	hr	

Rear Temperature	254 to 293	°C
Middle Temperature	260 to 293	°C
Front Temperature	266 to 293	°C
Nozzle Temperature	271 to 293	°C
Processing (Melt) Temp	271 to 293	°C
Mold Temperature	93.3 to 113	°C
Injection Rate	Slow-Moderate	
Screw Speed	20 to 100	rpm
Clamp Tonnage	5.5 to 8.3	kN/cm ²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

