

# KetaSpire® KT-851

Polyetheretherketone

Solvay Specialty Polymers

## Message:

KetaSpire® KT-851 resin is a depth-filtered grade of polyetheretherketone (PEEK) specially designed for use in extruded wire insulation coating. KT-851 offers the needed balance of properties and processability for applying thin insulation coatings onto copper or other conducting wire using a continuous extrusion process to achieve a robust insulation coating that is capable of withstanding the harsh use environments of many industrial applications. KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent chemical resistance to organics, acids and bases, best in class fatigue resistance, excellent wear resistance, ease of melt processing and high purity. The pellets are supplied with a very light dusting (0.01%) of calcium stearate to aid with conveying through single screw extruder-based processing equipment.

Natural: KetaSpire® KT-851 NT

| General Information |                                    |
|---------------------|------------------------------------|
| UL YellowCard       | E140728-100211982                  |
| Additive            | Lubricant                          |
| Features            | Good dimensional stability         |
|                     | Impact resistance, good            |
|                     | Good chemical resistance           |
|                     | Fatigue resistance                 |
|                     | Heat resistance, high              |
|                     | ductility                          |
|                     | Flame retardancy                   |
|                     |                                    |
|                     |                                    |
|                     |                                    |
| Uses                | Electrical/Electronic Applications |
|                     | Wire sheath                        |
|                     | Oil/Gas Supplies                   |
| RoHS Compliance     | Contact manufacturer               |
| Appearance          | Natural color                      |
| Forms               | Particle                           |
| Processing Method   | Machining                          |
|                     | Profile extrusion molding          |
|                     | Injection molding                  |

| Physical                                  | Nominal Value | Unit              | Test Method |
|---|---------------|-------------------|-------------|
| Specific Gravity                          | 1.30          | g/cm <sup>3</sup> | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (400°C/2.16 kg) | 10            | g/10 min          | ASTM D1238  |
| Molding Shrinkage                         |               |                   | ASTM D955   |
| Flow                                      | 1.1 - 1.3     | %                 | ASTM D955   |
| Transverse flow                           | 1.3 - 1.5     | %                 | ASTM D955   |
| Water Absorption (24 hr)                  | 0.10          | %                 | ASTM D570   |

| Hardness  | Nominal Value | Unit              | Test Method         |
|---|---------------|-------------------|---------------------|
| Rockwell Hardness (M-Scale)   | 97            |                   | ASTM D785           |
| Durometer Hardness (Shore D, 1 sec)   | 88            |                   | ASTM D2240          |
| Mechanical  | Nominal Value | Unit              | Test Method         |
| Tensile Modulus   |               |                   |                     |
| -- <sup>1</sup>   | 3600          | MPa               | ASTM D638           |
| --  | 3850          | MPa               | ISO 527-2/1A/1      |
| Tensile Stress  |               |                   |                     |
| Yield   | 95.0          | MPa               | ISO 527-2/1A/50     |
| --  | 96.0          | MPa               | ASTM D638           |
| Tensile Elongation  |               |                   |                     |
| Yield <sup>2</sup>  | 5.2           | %                 | ASTM D638           |
| Yield   | 4.8           | %                 | ISO 527-2/1A/50     |
| Fracture <sup>3</sup>   | 20 - 30       | %                 | ASTM D638           |
| Fracture  | 20 - 30       | %                 | ISO 527-2/1A/50     |
| Flexural Modulus  |               |                   |                     |
| --  | 3900          | MPa               | ASTM D790           |
| --  | 3620          | MPa               | ISO 178             |
| Flexural Strength   |               |                   |                     |
| --  | 152           | MPa               | ASTM D790           |
| --  | 112           | MPa               | ISO 178             |
| Compressive Strength  | 121           | MPa               | ASTM D695           |
| Shear Strength  | 91.5          | MPa               | ASTM D732           |
| Impact  | Nominal Value | Unit              | Test Method         |
| Notched Izod Impact   |               |                   |                     |
| --  | 69            | J/m               | ASTM D256           |
| --  | 7.5           | kJ/m <sup>2</sup> | ISO 180             |
| Unnotched Izod Impact   | No Break      |                   | ASTM D4812, ISO 180 |
| Thermal   | Nominal Value | Unit              | Test Method         |
| Deflection Temperature Under Load <sup>4</sup> (1.8 MPa, Annealed, 3.20 mm) | 157           | °C                | ASTM D648           |
| Glass Transition Temperature  | 150           | °C                | ASTM D3418          |
| Peak Melting Temperature  | 340           | °C                | ASTM D3418          |
| CLTE - Flow (-50 to 50°C)   | 4.3E-5        | cm/cm/°C          | ASTM E831           |
| Specific Heat   |               |                   |                     |
| 50°C  | 1350          | J/kg/°C           | DSC                 |
| 200°C   | 1950          | J/kg/°C           | DSC                 |
| Thermal Conductivity  | 0.24          | W/m/K             | ASTM E831           |
| Electrical  | Nominal Value | Unit              | Test Method         |
| Surface Resistivity   | > 1.9E+17     | ohms              | ASTM D257           |
| Volume Resistivity  | 2.5E+17       | ohms · cm         | ASTM D257           |
| Dielectric Strength (0.0500mm, amorphous film)                              | 200           | kV/mm             | ASTM D149           |

| Fill Analysis                                   | Nominal Value | Unit | Test Method |
|---|---------------|------|-------------|
| Melt Viscosity (400°C, 1000 sec <sup>-1</sup> ) | 380           | Pa·s | ASTM D3835  |

#### Additional Information

##### Standard Packaging and Labeling

KetaSpire resins are packaged in polyethylene buckets or cardboard boxes depending upon the order size. Individual packages will be plainly marked with the product, color, lot number, and net weight.

| Injection               | Nominal Value     | Unit |
|-------------------------|-------------------|------|
| Drying Temperature      | 150               | °C   |
| Drying Time             | 4.0               | hr   |
| Rear Temperature        | 355               | °C   |
| Middle Temperature      | 365               | °C   |
| Front Temperature       | 370               | °C   |
| Nozzle Temperature      | 375               | °C   |
| Mold Temperature        | 175 - 205         | °C   |
| Injection Rate          | Fast              |      |
| Screw Compression Ratio | 2.5:1.0 - 3.5:1.0 |      |

#### Injection instructions

##### Drying

KetaSpire resins must be dried completely prior to melt processing. Incomplete drying will result in defects in the formed part ranging from surface streaks to severe bubbling. Pellets can be dried on trays in a circulating air oven or in desiccating hopper dryer. Drying conditions recommended are 4 hours at 150°C (300°F) .

##### Injection Molding

KetaSpire resins can be readily injection molded in most screw injection machines. A general purpose screw with a compression ratio in the range of 2.5 - 3.5 : 1 is recommended, as is minimum back pressure. Injection speeds should be as fast as possible, consistent with part appearance requirements. Mold temperatures in the range of 175°C to 205°C (350°F to 400°F) are suggested. Recommended starting point barrel temperatures are shown in the following table.

| NOTE |                |
|------|----------------|
| 1.   | 1.0 mm/min     |
| 2.   | 50 mm/min      |
| 3.   | 50 mm/min      |
| 4.   | 200°C, 2 hours |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT