

Hiprolon® 200 VN LM

Polyamide 1010

Arkema

Message:

Hiprolon ® 200 VN LM is a polyamide produced from a renewable source. This grade is a polyamide 10.10 neat resin.

General Information			
Features	Renewable Resource Content		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1600	MPa	ISO 527-2
Tensile Stress (Yield)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	> 50	%	ISO 527-2
Flexural Modulus	1200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	11	kJ/m²	
23°C	16	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	202	°C	ISO 11357-3
Additional Information	Nominal Value	Unit	Test Method
ISO Shortname	PA 1010, 22-020		ISO 1874
Renewable Carbon Conent	> 99	%	ASTM D6866
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	220 to 280	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	4.0	hr	
Melt Temperature	210 to 260	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

