

HiFill® PPSU GY061

Polyphenylsulfone
Techmer Engineered Solutions

Message:

HiFill® PPSU GY061 is a Polyphenylsulfone (PPSU) product. It can be processed by injection molding and is available in North America. Primary characteristic: flame rated.

General Information			
Appearance	Colors Available		
	Grey		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/1.05 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.70	%	ASTM D955
Water Absorption (24 hr)	1.1	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	69.6	MPa	ASTM D638
Tensile Elongation (Yield)	7.0	%	ASTM D638
Flexural Modulus	2450	MPa	ASTM D790
Flexural Strength	88.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	207	°C	ASTM D648
CLTE - Flow	7.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹	19	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.57 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	160	°C	
Drying Time	3.0	hr	
Rear Temperature	357 to 391	°C	
Middle Temperature	357 to 391	°C	

Front Temperature	357 to 391	°C
Processing (Melt) Temp	343 to 399	°C
Mold Temperature	110 to 149	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	50 to 100	rpm

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

