

KIBITON® TPE PB-5302

Thermoplastic Elastomer

CHI MEI CORPORATION

Message:

KIBITON® TPE PB-5302 is a Thermoplastic Elastomer (TPE) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: rohs compliant.

General Information			
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.938	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/5.0 kg	9.0	g/10 min	
200°C/5.0 kg	12	g/10 min	
Ash Content	0.2	wt%	ASTM D1416
Oil Content	0.0	phr	ASTM D1416
Volatile Matter	0.40	wt%	ASTM D1416
Bale Weight	20000	g	
BD/SM Ratio	68/32	wt%	ASTM D1416
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	72		ASTM D2240
Injection	Nominal Value	Unit	
Rear Temperature	130 to 150	°C	
Middle Temperature	140 to 180	°C	
Front Temperature	140 to 180	°C	
Processing (Melt) Temp	150 to 160	°C	
Mold Temperature	30.0 to 70.0	°C	
Injection Pressure	1.96 to 7.85	MPa	
Holding Pressure	1.96 to 3.92	MPa	
Back Pressure	0.490 to 0.981	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

