COSMOPLENE® FL7641

Polypropylene Random Copolymer

TPC, The Polyolefin Company (Singapore) Pte Ltd

Message:

COSMOPLENE®FL7641 is a polypropylene random copolymer (PP random copolymer) product. It can be processed by casting film and is available in the Asia-Pacific region. COSMOPLENE®FL7641 applications include movies and glue/gummed paper. Features include: Strong adhesion high gloss Copolymer

General Information			
Features	Highlight		
	Good adhesion		
	Terpolymer		
	Random copolymer		
Uses	cast film		
	Adhesive		
Forms	Particle		
Processing Method	cast film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR)	7.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	44.1	MPa	ASTM D638
Tensile Elongation (Yield)	900	%	ASTM D638
Apparent Bending Modulus	830	MPa	ASTM D747
Thermal	Nominal Value	Unit	
Melting Temperature	139	°C	
Additional Information			
Chill Roll Temperature: 30 to 50°CCast Fi	lm Heat Seal Temperature: 120°C		
Extrusion	Nominal Value	Unit	
Melt Temperature	230 - 250	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

