

HANWHA EVA 1826

Ethylene Vinyl Acetate Copolymer

Hanwha Chemical

Message:

HANWHA EVA 1826 is manufactured by high pressure autoclave process and designed for base resin of variety of wire & cable compounds such as semi-conductive compound, flame retardant compound. EVA 1826 is well known for its excellent processability, filler loadability and high quality assurance.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Copolymer		
	Good Processability		
	High Elasticity		
Uses	Wire & Cable Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.949	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5	g/10 min	ASTM D1238
Vinyl Acetate Content	26.0	wt%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	82		
Shore D, 1 sec	28		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	16.7	MPa	ASTM D638
Tensile Elongation (Break)	800	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	48.0	°C	ASTM D1525
Melting Temperature	76.0	°C	ASTM D3417
Additional Information	Nominal Value	Unit	
Processing Temperature			
Kneader	90 to 110	°C	
Roll Mill	100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

