

Pebax® 2533 SN 01

Polyether Block Amide

Arkema

Message:

Pebax® 2533 SN 01 is a Polyether Block Amide (PEBA-Ether) product. It can be processed by blow molding, calendering, casting, coating, extrusion, film extrusion, injection molding, profile extrusion, resin transfer molding, sheet extrusion, or thermoforming and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Good UV Resistance

Heat Resistant

Impact Resistant

General Information				
Features		Good Impact Resistance		
		Good UV Resistance		
		High Heat Resistance		
		Platable		
Appearance		Clear/Transparent		
Forms		Granules		
Processing Method		Blow Molding		
		Calendering		
		Casting		
		Coating		
		Extrusion		
		Film Extrusion		
		Injection Molding		
		Profile Extrusion		
		Resin Transfer Molding		
		Sheet Extrusion		
		Thermoforming		
Multi-Point Data		Isochronous Stress vs. Strain (ISO 11403-1)		
		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Dry	Conditioned	Unit	Test Method
Density	1010	1010	kg/m ³	ISO 1183 ¹
Melt volume-flow rate (235°C/1.0 kg)	14.0	--	cm ³ /10min	ISO 1133 ²
Water Absorption				ISO 62 ³

Saturation	1.2	--	%	
Equilibrium	0.50	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (50% Strain)	3.00	3.00	MPa	ISO 527-2 ⁴
Tensile Strain (Break)	> 50	> 50	%	ISO 527-2 ⁵
Impact	Dry	Conditioned	Unit	Test Method
Charpy notched impact strength				ISO 179/1eA ⁶
-30°C	--	No Break		
23°C	--	No Break		
Charpy impact strength				ISO 179/1eU ⁷
-30°C	--	No Break		
23°C	--	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	42.0	--	°C	ISO 75-2 ⁸
Melting Temperature ⁹	134	--	°C	ISO 11357-3 ¹⁰
CLTE - Flow	2.0E-4	--	cm/cm/°C	ISO 11359-2 ¹¹
Electrical	Dry	Conditioned	Unit	Test Method
Surface resistivity	--	3.0E+12	ohms	IEC 60093 ¹²
Volume resistivity	1.3E+10	--	ohms·m	IEC 60093 ¹³
Electric strength	36	--	kV/mm	IEC 60243-1 ¹⁴
Relative Permittivity				IEC 60250 ¹⁵
100 Hz	6.00	--		
1 MHz	6.00	--		
Dissipation Factor				IEC 60250 ¹⁶
100 Hz	0.055	--		
1 MHz	0.038	--		
Comparative tracking index	--	600		IEC 60112 ¹⁷
Flammability	Dry	Conditioned	Unit	Test Method
Burning Behav. at 1.6mm nom. thickn. (1.60 mm, UL)	HB	--		ISO 1210 ¹⁸
NOTE				

1.

Tested in accordance with
ISO 10350. 23°C/50%r.h.
unless otherwise noted.

2.

Tested in accordance with
ISO 10350. 23°C/50%r.h.
unless otherwise noted.

3.

Tested in accordance with
ISO 10350. 23°C/50%r.h.
unless otherwise noted.

4.

Tested in accordance with
ISO 10350. 23°C/50%r.h.
unless otherwise noted.

5.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
6.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
7.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
8.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
9.	10 °C/min
10.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
11.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
12.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
13.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
14.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
15.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
16.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
17.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
18.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT