SPI CPPFG18CNAT

Polypropylene Impact Copolymer

Service Polymers, Inc.

Message:

SPI CPPFG18CNAT is a Polypropylene Impact Copolymer (PP Impact Copolymer) product filled with 18% glass fiber. It is available in North America. Characteristics include: Flame Rated Chemically Coupled Copolymer

General Information			
Filler / Reinforcement	Glass Fiber,18% Filler by Weigh	t	
Features	Chemically Coupled		
	Impact Copolymer		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3960 to 5170	MPa	ASTM D638
Tensile Strength (Yield)	51.7 to 65.5	MPa	ASTM D638
Tensile Elongation (Yield)	2.0 to 4.0	%	ASTM D638
Flexural Modulus	2930 to 3620	MPa	ASTM D790
Flexural Strength (Yield)	82.7 to 93.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53 to 91	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	9.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (3.00 mm)	НВ		UL 94
Injection	Nominal Value	Unit	
Dew Point	-17.8	°C	
Suggested Max Moisture	0.15	%	
Processing (Melt) Temp	191 to 232	°C	
Mold Temperature	32.2 to 65.6	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

