

Lupoy® GN2201FM

Polycarbonate

LG Chem Ltd.

Message:

Description

Halogen Free Flame Retardant, Heat Resistance

Application

IT/OA, Electric & Electronic Housing and Components

General Information			
UL YellowCard	E67171-248614	E248280-322191	E353371-101107272
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Flame Retardant		
	Halogen Free		
	High Heat Resistance		
Uses	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.10 to 0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	108	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	3.0	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	5880	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	167	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵ (0.45 MPa, Unannealed, 6.40 mm)	142	°C	ASTM D648
RTI Elec	120	°C	UL 746
RTI Imp	90.0	°C	UL 746
RTI Str	105	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	V-0		

V-0

3.00 mm

5VA

Injection	Nominal Value	Unit
Drying Temperature	100 to 200	°C
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	< 0.020	%
Rear Temperature	270 to 300	°C
Middle Temperature	280 to 310	°C
Front Temperature	290 to 330	°C
Nozzle Temperature	290 to 330	°C
Processing (Melt) Temp	300 to 340	°C
Mold Temperature	90.0 to 120	°C
Back Pressure	0.981 to 3.92	MPa
Screw Speed	40 to 70	rpm

NOTE

- | | |
|----|------------|
| 1. | 5.0 mm/min |
| 2. | 5.0 mm/min |
| 3. | 1.3 mm/min |
| 4. | 1.3 mm/min |
| 5. | 18.6kg |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT