Mylar® A (48 guage)

Polyethylene Terephthalate

DuPont Teijin Films U.S.

Message:

Mylar Type A films have balanced tensile properties and excellent resistance to moisture and most chemicals. They can withstand temperature extremes from -94 to 302°F. Mylar does not become brittle with age under normal conditions, because it contains no plasticizers.

General Information					
UL YellowCard	E93687-252918				
Features	General Purpose				
	Good Adhesion				
	Good Chemical Resistance				
	Good Processability				
	Good Thermal Stability				
	Good Toughness				
	Moisture Resistant				
	Non-Smooth Surface Finish				
Uses	Carbon Ribbons				
	Film				
	Labels				
	Liners				
	Protective Coverings				
	Таре				
Appearance	Clear/Transparent				
Forms	Film				
Physical	Nominal Value	Unit	Test Method		
Density	1.39	g/cm³	ASTM D1505		
Molding Shrinkage			ASTM D955		
Flow : 0.0119 mm	2.0	%			
Across Flow: 0.0119 mm	1.0	%			
Films	Nominal Value	Unit	Test Method		
Film Thickness - Tested	12	μm			
Tensile Strength			ASTM D882		
MD : Yield	179	MPa			
TD : Yield	221	MPa			
Tensile Elongation			ASTM D882		
MD : Break	110	%			
TD : Break	70	%			

Optical	Nominal Value	Unit	Test Method
Haze	4.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

