

PROTEQ™ H20SQ8

Polypropylene Homopolymer

Marplex Australia Pty. Ltd.

Message:

PROTEQ™ H20SQ8 is a 40% highly coupled glass fibre reinforced homopolymer polypropylene compound. This grade has a combination of high stiffness and tensile strength coupled with high impact strength and contains stabilisers for heat resistance. These properties give the material excellent creep resistance and long term durability as well as high physical strength.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	Chemically Coupled		
	Durable		
	Good Creep Resistance		
	High Impact Resistance		
	High Stiffness		
	High Strength		
	Homopolymer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	0.40	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	79		
Shore D, 15 sec	74		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.20 mm)	112	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	3.0	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	7750	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C, 3.20 mm	75	J/m	
23°C, 3.20 mm	100	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.20 mm	157	°C	
1.8 MPa, Unannealed, 3.20 mm	146	°C	
Vicat Softening Temperature	167	°C	ASTM D1525 ⁴

CLTE - Flow	2.8E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Ignition Temperature (1.60 mm)	550	°C	AS/NZS 60695
Injection	Nominal Value	Unit	
Drying Temperature	85.0 to 90.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	215 to 235	°C	
Middle Temperature	235 to 255	°C	
Front Temperature	245 to 265	°C	
Processing (Melt) Temp	230 to 270	°C	
Mold Temperature	40.0 to 70.0	°C	
Injection Pressure	160 to 250	MPa	
Injection Rate	Moderate-Fast		
Back Pressure	0.100 to 0.500	MPa	
Screw Speed	40 to 60	rpm	
Clamp Tonnage	3.0 to 6.0	kN/cm ²	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	10 mm/min		
4.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

