

Dynaflex™ G2703-1000-00

Thermoplastic Elastomer

PolyOne Corporation

Message:

Dynaflex™G2703-1000-00 is an easy-to-process TPE designed for injection molding and extrusion molding applications that require compliance with FDA standards and low friction coefficient.

can be bonded to polypropylene

Excellent coloring

Strong ozone resistance and UV resistance

improved demoulding performance

Similar to rubber

Soft to the touch

General Information			
Features	Low friction coefficient		
	Good UV resistance		
	Recyclable materials		
	Good coloring		
	Ozone resistance		
	Good demoulding performance		
Uses	overmolding		
	Personal care		
	Soft touch application		
	Transparent or Translucent Accessories		
	Consumer goods application field		
Agency Ratings	FDA Not Rated 2		
RoHS Compliance	RoHS compliance		
Appearance	Translucent		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	4.0	g/10 min	ASTM D1238
200°C/5.0 kg	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.90 - 1.5	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	60		ASTM D2240

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ASTM D412
100% strain, 23°C ²	2.14	MPa	ASTM D412
300% strain, 23°C ³	3.54	MPa	ASTM D412
Tensile Strength (Break, 23°C)	7.38	MPa	ASTM D412
Tensile Elongation (Break, 23°C)	700	%	ASTM D412
Tear Strength	31.5	kN/m	ASTM D624
Compression Set (23°C, 22 hr)	21	%	ASTM D395B
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 11200 sec ⁻¹)	10.7	Pa·s	ASTM D3835

Additional Information

Dynaflex™ G2703-1000-00 can be recycled as a filler or impact modifier for polyolefins, or can be recycled by grinding and reintroduction to the molding process. Similar to PP or PE recycling process, if separated appropriately, it can be recycled many times. Municipality waste stream recycle code is "7" which is designated for "Other". Please contact GLS Thermoplastic Elastomers for a copy of our Recyclability Compliance letter.

Injection	Nominal Value	Unit
Rear Temperature	160 - 177	°C
Middle Temperature	171 - 188	°C
Front Temperature	177 - 216	°C
Nozzle Temperature	177 - 216	°C
Mold Temperature	15.6 - 37.8	°C
Back Pressure	0.00 - 1.03	MPa
Screw Speed	40 - 100	rpm

Injection instructions

以聚丙烯 (PP), 乙烯醋酸乙烯共聚物 (EVA) 或低密度聚乙烯 (LDPE) 为基础的色母料最适合 Dynaflex™ G2703-1000-00 着色. 使用熔体流动速率较高(范围为 25 - 40 克/10 分钟)的色母料, 则能达到较好的颜色分散效果. 典型的色母料用量为 1% 至 5%(重量). 可以使用液体颜料, 但以矿物油为基础的载体对最终硬度值会有显著的影响. 不应采用以 PVC 为基础的色母料. 若使用 GLS 可供的预着色复合材料, 则可达到较好的配色一致性. 色母料是否适用, 应由用户通过试验来最终确定. 在使用此产品之前或之后, 均须用熔体流动速率较低 (0.5 - 2.5 MFR) 的聚乙烯 (PE) 或聚丙烯 (PP) 彻底进行置换. Dynaflex™ G2703-1000-00 具有极好的熔体稳定性. 最长停留时间可能会根据机筒尺寸有所变化. 通常, 如果机器闲置 8 - 10 分钟或以上, 则应将机筒排空. 不需要干燥注射速度: 1 - 5 英寸/秒 第一阶段 - 提升压力: 200 - 600 psi 第二阶段 - 保持压力: 70% 的升压保持时间(厚部件): 4 - 10 秒 保持时间(薄部件): 1 - 3 秒

NOTE

1. 2 hours
2. Mouth die c
3. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT