TechnoElast 9080

Styrene Ethylene Butylene Styrene Block Copolymer

TechnoCompound GmbH

Message:

The TechnoElast TPE compounds are a new, innovative product range of TechnoCompound based on styrene block copolymers. TechnoElast TPE compounds with adjustable melt flow rates possess good insulation properties, good workability, offer good thermal stability, outstanding absorption characteristics as well as elastic memory.

General Information					
Features	Block Copolymer				
	Resilient recovery, excellent Good liquidity				
	Thermal stability, good				
Uses	Membrane key switch				
	Electrical/Electronic Applications				
	Electrical housing				
	Insulating material				
	Seals				
	Parts under the hood of a car				
	Application in Automobile Field				
	Car interior parts				
	Automotive exterior parts				
	Shell				
Forms	Particle				
Processing Method	Injection molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.14	g/cm³	ISO 1183		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	80		ISO 868		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress (Break)	10.0	MPa	ISO 527-2		
Tensile Strain (Break)	250	%	ISO 527-2		

The value listed as Shore Hardness, ISO 868, was tested in accordance with DIN 53505. The value listed as Tensile Stress at Break, ISO 527-1, -2, was tested in accordance with DIN 53504. The value listed as Tensile Strain at Break, ISO 527-1, -2, was tested in accordance with DIN 53504. Moisture Content, Infared 105°C, 15 min: 250%

Injection	Nominal Value	Unit
Drying Temperature	60.0 - 80.0	°C
Drying Time	2.0	hr

Processing (Melt) Temp	180 - 220	°C	
Mold Temperature	20.0 - 40.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2