MARPOL® PET IV 80 WB

Polyethylene Terephthalate

Marco Polo International, Inc.

Message:

Features: Good processability Excellent clarity/gloss Properties balanced for wide range of general purpose usages. It is typically used for: Various foods, beverages, water etc. Containers for FMCG such as cosmetics, hair-oil, disinfectants Pharmaceuticals APET sheet and PET strapping Certifications:

PET Marpol IV 80 WB resin is considered safe for food-packaging applications based on compliance with FDA regulation 21 CFR Section 177.1630 & other similar food contact safety regulations.

General Information							
Features	Food Contact Acceptable Good Processability						
	High Clarity						
	High Gloss						
Uses	Containers						
	Cosmetic Packaging						
	Food Containers Non-specific Food Applications Pharmaceuticals Sheet						
					Strapping		
				Agency Ratings	FDA 21 CFR 177.1630		
Physical	Nominal Value	Unit	Test Method				
Acetaldehyde	1.0	ppm	Internal Method				
Color b - CIE	-3.00 to 0.00		Internal Method				
Crystallinity	50	%	Internal Method				
Intrinsic Viscosity	0.80	dl/g	Internal Method				
Chips/Gram	72.0		Internal Method				
Fines	100	ppm	Internal Method				

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

