

Mirathane™ E385

Thermoplastic Polyurethane Elastomer (Polyester)

Miracll Chemicals Co., Ltd.

Message:

Mirathane™ E385 is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) product. It is available in Asia Pacific. Applications of Mirathane™ E385 include additive/masterbatch, hose/tubing, consumer goods and engineering/industrial parts.

Characteristics include:

Fast Molding Cycle

Good Processability

General Information	
Features	Fast Molding Cycle
	Good Processability
	Low to No Migration
Uses	Compounding
	Footwear
	Hose
	Overmolding
	Plastics Modification
	Tubing
	Wheels

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	87		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	6.00	MPa	
300% Strain	10.0	MPa	
Tensile Strength (Yield)	30.0	MPa	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Tear Strength	90.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-25.0	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

