Clearflex® RN 50 U

Linear Medium Density Polyethylene

Versalis S.p.A.

Message:

Clearflex RN 50 U is a linear medium density polyethylene resin, with antioxidants and UV stabilizers, suitable for rotomoulding applications. Items manufactured with Clearflex RN 50 U show good mechanical properties and excellent surface aspect. Main Application

Thanks to high processability, Clearflex RN 50 U is recommended for the production for hardly shaped items, vases and garden articles.

General Information				
Additive	Antioxidant			
	UV Stabilizer			
Features	Antioxidant			
	Food Contact Acceptable			
	Good Processability			
	Good Surface Finish			
	Good UV Resistance			
	Medium Density			
Uses	Containers			
	Lawn and Garden Equipment			
Agency Ratings	EU Food Contact, Unspecified Rating			
Forms	Pellets	Pellets		
Processing Method	Rotational Molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.936	g/cm³	ISO 1183	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	6.0	g/10 min	ISO 1133	
Environmental Stress-Cracking Resistance (Injection Molded)	> 250	hr	ISO 22088	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore D, Injection Molded)	54		ISO 868	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress			ISO 527-2	
Yield, Injection Molded	18.0	MPa		
Break, Injection Molded	17.0	MPa		
Tensile Strain (Break, Injection Molded)	> 700	%	ISO 527-2	
Flexural Modulus (Injection Molded)	650	MPa	ISO 178	
Impact	Nominal Value	Unit	Test Method	

Drop Impact Resistance (Rotomolded			
Specimen)	210	J/cm	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	113	°C	ISO 306/A
Melting Temperature	127	°C	Internal Method
Injection	Nominal Value	Unit	
Processing (Melt) Temp	230 to 280	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

