

VENYL UG301 - 8070

Polyamide 66

AD majoris

Message:

VENYL UG301 - 8070 is a 30% glass fibre reinforced polyamide 66 with heat resistance for Injection moulding.

APPLICATIONS

VENYL UG301 - 8070 has been developed especially for very demanding applications in automotive industry and electrical parts requiring excellent combination between thermal and mechanical properties.

VENYL UG301 - 8070 is available in natural (VENYL UG301) and other colours can be provided on request.

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		High Heat Resistance		
		Recyclable Material		
Uses		Automotive Applications		
		Electrical Parts		
Appearance		Colors Available		
		Natural Color		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183
Molding Shrinkage	0.50 to 0.80	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.6	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (L-Scale)	110	108		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9000	6250	MPa	ISO 527-2
Tensile Stress (Break)	175	120	MPa	ISO 527-2
Tensile Strain (Break)	3.0	3.0	%	ISO 527-2
Flexural Modulus	8250	5500	MPa	ISO 178
Flexural Stress	260	215	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	9.0	13	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	35	45	kJ/m ²	ISO 179
Notched Izod Impact	95	130	J/m	ISO 180

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	260	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	250	--	°C	ISO 75-2/A
Melting Temperature (DSC)	256	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+11	ohms	DIN 53482
Volume Resistivity	1.0E+14	1.0E+12	ohms·cm	DIN 53482
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index	24	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	90.0		°C	
Drying Time	4.0		hr	
Rear Temperature	285 to 300		°C	
Middle Temperature	280 to 295		°C	
Front Temperature	275 to 290		°C	
Nozzle Temperature	265 to 280		°C	
Mold Temperature	90.0 to 120		°C	
Injection Pressure	85.0 to 110		MPa	
Injection Rate	Fast			
Holding Pressure	50.0 to 70.0		MPa	
Screw L/D Ratio	15.0:1.0 to 20.0:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT