

Petrothene® LH735000

High Density Polyethylene

LyondellBasell Industries

Message:

Petrothene LH735000 exhibits an excellent balance of stiffness and environmental stress crack resistance. Typical applications include bottles for bleach, detergents and household chemicals.

| General Information | | |
|---|--|-------------------|
| Features | Rigid, good | |
| | High ESCR (Stress Cracking Resistance) | |
| Uses | Bottle | |
| Processing Method | Extrusion blow molding | |
| Physical | Nominal Value | Unit |
| Density (23°C) | 0.953 | g/cm ³ |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 0.35 | g/10 min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

