

Plenco 02308 (Injection)

Phenolic
Plastics Engineering Co.

Message:

PLENCO 02308 is a general purpose organic filled phenolic molding compound, offering improved heat resistance and optimized cure properties. UL recognized under component file E40654. 02308 is available in black or brown color.

General Information			
UL YellowCard	E40654-231584		
Filler / Reinforcement	Organic filler		
Features	Fast curing		
	Heat resistance, high		
	General		
Uses	General		
UL File Number	E40654		
Appearance	Brown		
	Black		
Forms	Particles		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792
Apparent Density	0.62	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	1.1	%	ASTM D955
Water Absorption (24 hr)	0.32	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (E-Scale)	82		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8640	MPa	ASTM D638
Tensile Strength	58.0	MPa	ASTM D638
Tensile Elongation (Break)	0.70	%	ASTM D638
Flexural Modulus	7470	MPa	ASTM D790
Flexural Strength	88.0	MPa	ASTM D790
Compressive Strength	190	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	18.1	J/m	ASTM D256
Notched Izod Impact	15	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	141	°C	ASTM D648

Continuous Use Temperature	199	°C	ASTM D794
CLTE - Flow	5.9E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.4E+11	ohms·cm	ASTM D257
Dielectric Strength ¹	11	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	4.90		ASTM D150
Dissipation Factor (1 MHz)	0.053		ASTM D150
Arc Resistance	142	sec	ASTM D495
Comparative Tracking Index (CTI)	175	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Oxygen Index	25	%	ASTM D2863
Additional Information			
The value listed as Mold Shrink, Linear-Flow, ASTM D955 was tested according to the ASTM D6289 standard.The value listed as Comparative Tracking Index, UL 746 was tested according to ASTM D3638.Post Shrinkage, ASTM D6289, 72hr, 120°C: 0.33%Heat Resistance, ASTM D794: 199°CDrop Ball Impact, PLENCO Method: 89 J/m			
Injection	Nominal Value	Unit	
Suggested Shot Size	20 - 80	%	
Rear Temperature	66.0 - 82.0	°C	
Front Temperature	82.0 - 99.0	°C	
Processing (Melt) Temp	104 - 115	°C	
Mold Temperature	165 - 182	°C	
Injection Pressure	6.20 - 11.0	MPa	
Back Pressure	0.300	MPa	
Screw Speed	< 60	rpm	
Cushion	3.00	mm	
Injection instructions			
Injection Time: 3-8 sec			
NOTE			
1.	Method A (short time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT