

# Baytec® 5340

Polyurethane Thermoset Elastomer

Covestro - PUR

## Message:

Baytec 5340 system is designed for edge molding applications, and forms a tough, durable elastomer that is cut and mar resistant with a hardness of 65 Shore A. As with any product, use of Baytec 5340 system in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability for use.

General Information		
Forms	Liquid	
Hardness	Nominal Value	Test Method
Durometer Hardness (Shore A)	65	ASTM D2240
Thermoset	Nominal Value	
Thermoset Components		
Component a	Mixing ratio by weight: 32	
Component B	Mixing ratio by weight: 100	
Additional Information		
Part A		
Type: Isocyanate		
Appearance: Clear liquid		
Specific Gravity: 1.21		
Viscosity: 550 to 800 cps		
Part B		
Type: Polyol		
Appearance: White liquid		
Specific Gravity: 1.09		
Viscosity: 750 to 150 cps		
Gel Time: 55 to 65 secIsocyanate Component Temperature: 75 to 95°FPolyol Component Temperature: 75 to 95°F		
Mold Temperature: 120 to 160°F		
Demold Time: Up to 10 minutes		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

