

Ravathane R210A85UV

Thermoplastic Polyurethane Elastomer (Polyether)

RAVAGO Kimya Plastik Sanayi ve Ticaret A.S.

Message:

Description: Product is based on standard grade polyether and has strong resilience and tear resistance, excellent abrasion resistance, excellent resistance to hydrolysis failure and microbial attack, good stability towards solvents and light.

Application: Injection molding and extrusion

General Information			
Features	Antimicrobial		
	Good tear strength		
	Good wear resistance		
	Hydrolysis resistance		
	Elastic		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	85		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Abrasion Resistance	35.0	mm ³	ISO 4649
Extruder Screw L/D Ratio	25:1		
Screw cooling	Air		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% strain	7.00	MPa	ISO 37
300% strain	13.0	MPa	ISO 37
Tensile Stress (Yield)	33.0	MPa	ISO 37
Tensile Elongation (Break)	650	%	ISO 37
Tear Strength ¹	100	kN/m	ISO 34-1
Injection	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Rear Temperature	195	°C	
Middle Temperature	205	°C	
Front Temperature	210	°C	
Nozzle Temperature	200	°C	
Injection Pressure	70.0	MPa	

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	185 - 200	°C
Cylinder Zone 2 Temp.	200 - 220	°C
Cylinder Zone 3 Temp.	210 - 230	°C
Cylinder Zone 4 Temp.	200 - 220	°C
Die Temperature	190 - 200	°C
Extrusion instructions		
Type: 30/25d, Screw: 3:1, Speed: 3:1, Speed: 50 rpm, Thickness Die: 0.2mm, Pre-heating: 1h@100°C		
NOTE		

- Method B, right-angle specimen
(cut)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

