

# Aristech Quarite Select Plus®

Acrylic

Aristech Acrylics LLC

## Message:

Aristech Quarite Select Plus® is an Acrylic material. It is available in North America for thermoforming.

Important attributes of Aristech Quarite Select Plus® are:

Flame Rated

Low to No Odor/Taste

General Information			
UL YellowCard	E87207-252290		
Features	Low to No Odor		
	Low to No Taste		
Forms	Sheet		
Processing Method	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Specific Gravity <sup>1</sup>	1.10	g/cm <sup>3</sup>	ASTM D792
Water Absorption <sup>2</sup> (Saturation, 7.11 mm)	0.19	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness <sup>3</sup> (M-Scale, 7.11 mm)	90 to 100		ASTM D785
Barcol Hardness <sup>4</sup> (7.11 mm)	48 to 52		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>5</sup> (7.11 mm)	2620	MPa	ASTM D638
Tensile Strength <sup>6</sup> (Yield, 7.11 mm)	39.3	MPa	ASTM D638
Tensile Elongation <sup>7</sup> (Break, 7.11 mm)	3.5	%	ASTM D638
Flexural Modulus <sup>8</sup> (7.11 mm)	2230	MPa	ASTM D790
Flexural Strength			ASTM D790
7.11 mm <sup>9</sup>	81.4	MPa	
7.11 mm <sup>10</sup>	70.3	MPa	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact <sup>11</sup> (7.11 mm)	120	J/m	ASTM D256A
Instrumented Dart Impact <sup>12</sup> (7.11 mm)	> 40.7	J	Internal Method
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load <sup>13</sup> (1.8 MPa, Unannealed, 7.11 mm)	87.8	°C	ASTM D648
CLTE - Flow <sup>14</sup> (7.11 mm)	8.1E-5	cm/cm/°C	ASTM D696
Thermal Stability (180°C, 6.99 to 7.24 mm) <sup>15</sup>	No Effect		ASTM D4802
Cycles Freeze-Thaw - 50 (-29 to 82°C, 6.99 to 7.24 mm)	No Effect		Internal Method
Hot Forming Temperature			Internal Method

ABS side : 6.99 to 7.24 mm	300 to 340	
Acrylic side : 6.99 to 7.24 mm	177 to 193	°C
Flammability	Nominal Value	Test Method
Flame Rating <sup>16</sup> (7.11 mm)	HB	UL 94
NOTE		
1.	0.275 to 0.285 in	
2.	0.275 to 0.285 in	
3.	0.275 to 0.285 in	
4.	0.275 to 0.285 in	
5.	0.275 to 0.285 in	
6.	0.275 to 0.285 in	
7.	0.275 to 0.285 in	
8.	0.275 to 0.285 in, Acrylic in Tension	
9.	0.275 to 0.285 in, Acrylic in Tension	
10.	0.275 to 0.285 in, Acrylic in Compression	
11.	0.275 to 0.285 in	
12.	0.275 to 0.285 in, FTMS 406 M-1074	
13.	0.275 to 0.285 in	
14.	0.275 to 0.285 in	
15.	30 min	
16.	0.275 to 0.285 in	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

