

MBA PS 3122

General Purpose Polystyrene

MBA Polymers

Message:

A post-consumer recycled polystyrene for general use. Available in standard grey (reference 70/15) and standard black (reference 90/04).

General Information			
Recycled Content	Yes		
Uses	General Purpose		
Appearance	Black		
	Grey		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	Internal Method
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	5.5	g/10 min	ISO 1133

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2350	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	25.0	MPa	ISO 527-2/50
Flexural Modulus (23°C)	2200	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.5	kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength (23°C)	7.0	kJ/m ²	ISO 180/1A

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	88.0	°C	ISO 306/B50

Injection	Nominal Value	Unit
Drying Temperature	70.0	°C
Drying Time	1.0 to 2.0	hr
Suggested Max Moisture	0.050 to 0.10	%
Processing (Melt) Temp	190 to 230	°C
Mold Temperature	20.0 to 60.0	°C

Extrusion	Nominal Value	Unit
Drying Temperature	70.0	°C
Drying Time	1.0 to 2.0	hr
Suggested Max Moisture	0.050 to 0.10	%
Melt Temperature	180 to 210	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

