

NEXUS PC PC1212FRRUV

Polycarbonate
Nexus Resin Group, LLC.

Message:
Molding Grade PC FR

General Information			
Additive	Flame Retardant		
	Mold Release		
	UV Stabilizer		
Features	Flame Retardant		
	Good Mold Release		
	Good UV Resistance		
UL File Number	E205256		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2380	MPa	ASTM D638
Tensile Strength (Yield)	58.6	MPa	ASTM D638
Flexural Modulus	2380	MPa	ASTM D790
Flexural Strength (Yield)	86.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	127	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	271 to 288	°C	
Middle Temperature	277 to 302	°C	
Front Temperature	288 to 316	°C	

Nozzle Temperature	288 to 316	°C
Processing (Melt) Temp	288 to 316	°C
Mold Temperature	76.7 to 104	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 75	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

