Axiall PVC 10870

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

General purpose non-lead stabilized jacket compound recommended for 60°C applications and also suited for 75°C at a wall thickness of 30 mils and larger.

General Information			
Features	General Purpose		
Uses	Cable Jacketing		
	Wire & Cable Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40 to 1.44	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	84 to 90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
	16.4	МРа	
100% Strain	9.65	МРа	
Tensile Elongation (Break)	340	%	ASTM D638
Aging	Nominal Value	Unit	Test Method
Change in Ultimate Elongation in Air ¹ (100°C, 240 hr)	-22	%	UL 1581
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-28.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	24	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Melt Temperature	188	°C	
NOTE			
1.	30 mil slabs		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

