

PERCOM® KMG40W

Polypropylene Copolymer

A. Schulman Europe

Message:

PERCOM® KMG40W is a Polypropylene Copolymer (PP Copolymer) material filled with 40% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of PERCOM® KMG40W are:

Flame Rated

RoHS Compliant

Copolymer

Impact Resistant

Typical applications include:

Household Applications

Plumbing/Piping/Potable Water

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	High Impact Resistance		
	Impact Copolymer		
Uses	Bathroom Accessories		
	Plumbing Parts		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Molding Shrinkage	0.20 to 0.50	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	70		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	85.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	5700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	18	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	157	°C	ISO 75-2/B
1.8 MPa, Unannealed	140	°C	ISO 75-2/A
Vicat Softening Temperature	166	°C	ISO 306/A50
Flammability	Nominal Value		Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

