

LITEN BB 85

Polyethylene Copolymer
UNIPETROL RPA

Message:

LITEN BB 85 is a copolymer with broad molecular weight distribution. It exhibits good toughness and impact and ESC resistance. Typical application is manufacture of containers up to 120 liters, such as bottles, canisters, barrels, etc. It can also be used for extrusion of films and sheets.

LITEN BB 85 meets the hygienic requirements on materials and articles intended for contact with foodstuffs according to Regulation (EC) 1935/2004 of the European Parliament and of the Council, as well as according to Commission Regulation (EU) No 10/2011 including changes and additions.

General Information			
Features	Copolymer		
	Food Contact Acceptable		
	Good Impact Resistance		
	Good Processability		
	Good Stiffness		
Uses	Bottles		
	Containers		
	Film		
	Sheet		
Agency Ratings	EC 1935/2004		
	EU 10/2011		
Forms	Pellets		
Processing Method	Film Extrusion		
	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.952	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	0.15	g/10 min	
190°C/21.6 kg	16	g/10 min	
190°C/5.0 kg	0.70	g/10 min	
Environmental Stress-Cracking Resistance (50°C, 100% Detergent, F50)	400	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	61		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	26.0	MPa	ISO 527-2
Tensile Strain (Yield)	9.0	%	ISO 527-2

Flexural Modulus	1150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	5.5	kJ/m ²	
23°C	13	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	125	°C	ISO 306

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT