

RTP ESD A 100 LF

Polypropylene
RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Features	Electrostatic discharge protection		
	Low liquidity		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.968	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm, Injection Molded)	1.0 - 2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	1170	MPa	ASTM D638
Tensile Strength	20.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	10	%	ASTM D638
Flexural Modulus (Injection Molded)	1030	MPa	ASTM D790
Flexural Strength (Injection Molded)	25.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm, Injection Molded)	750	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1400	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, Injection Molded)	43.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+11	ohms	ASTM D257
Volume Resistivity	5.0E+8	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Additional Information			

The value listed as Flammibility, UL 94, was tested in accordance with RTP Company methods.Static Decay MIL-PRF-81705D, FTMS-4046.1: 2 sec

Injection	Nominal Value	Unit
Rear Temperature	193 - 227	°C
Middle Temperature	193 - 227	°C
Front Temperature	193 - 227	°C
Mold Temperature	32.0 - 66.0	°C
Injection Pressure	69.0 - 103	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

