

# Huaфон JF-W-TL4140

Polyurethane  
Huaфон Group Co., Ltd.

Message:

TOL Reduction Wet Process PU Resin for Micro Fibre Leather

Characteristics

Hard type, acid and alkali resistance, hydrolysis resistance, good dyeing property, good elasticity, good film property, full of feeling, suit for TOL reduction technology.

Applications

For microfiber non-woven fabric

General Information	
Features	Acid Resistant
	Alkali Resistant
	High Elasticity
	High Hardness
	Hydrolysis Resistant
Uses	Fabrics
	Nonwovens

Additional Information	Nominal Value	Unit
Solvents	DMF	
Uncured Properties	Nominal Value	Unit
Solids Content	29 to 31	%
Viscosity (25°C)	100 to 160	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	13.0 to 15.0	MPa
Tensile Strength	> 30.0	MPa
Tensile Elongation at Break	> 300	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT