Texalan® 5 Series 565A

Thermoplastic Polyurethane Elastomer (Polyester)

Austin Novel Materials Co. Ltd.

Message:

Texalan® 5 Series 565A is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) material. It is available in Asia Pacific, Europe, or North America for blow molding, calendering, coextrusion, extrusion, or injection molding.

Important attributes of Texalan® 5 Series 565A are:

Chemical Resistant

High Strength

Impact Resistant

Low Temperature Resistant

Wear Resistant

General Information					
Features	Good Abrasion Resistance				
	High Elasticity				
	High Impact Resistance				
	High Tensile Strength				
	Low Temperature Resistant				
	Oil Resistant				
Processing Method	Blow Molding				
	Calendering				
	Coextrusion				
	Extrusion				
	Film Extrusion				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.04 to 1.08	g/cm³	ISO 1183		
Hardness	Nominal Value	Unit	Test Method		
Shore Hardness (Shore A)	62 to 68		ISO 868		

1 Trysical	Norminal Value	Offic	rest wethou
Density	1.04 to 1.08	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	62 to 68		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Abrasion Resistance	< 100	mm³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	> 1.00	MPa	
300% Strain	> 1.50	MPa	
Tensile Stress (Yield)	> 10.0	MPa	ISO 37
Tensile Elongation (Break)	> 800	%	ISO 37
Tensile Elongation (Break) Tear Strength	> 800 > 30	% kN/m	ISO 37 ISO 34-1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

