

Appeel® 20D855

Ethylene Acrylate Copolymer
DuPont Packaging & Industrial Polymers

Message:

DuPont™ Appeel 20D855 is a modified ethylene acrylate resin designed to function as a sealing layer for lidding applications. It is most often suggested to provide peelable seals over a broad temperature range to a number of container materials including PET, PVC, PS and PP. Appeel 20D855 is available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene resins.

General Information			
Uses	Cover		
	Seals		
Agency Ratings	FDA 21 CFR 177.1340		
Forms	Particle		
Processing Method	Co-extrusion molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0	g/10 min	ASTM D1238, ISO 1133
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	54.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	92.0	°C	ASTM D3418, ISO 3146
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	140	°C	
Cylinder Zone 2 Temp.	150	°C	
Cylinder Zone 3 Temp.	160	°C	
Cylinder Zone 4 Temp.	180	°C	
Cylinder Zone 5 Temp.	180	°C	
Adapter Temperature	180	°C	
Melt Temperature	160 - 185	°C	
Die Temperature	170	°C	
Extrusion instructions			

The above processing values are for blown film.Extrusion coating/lamination parameters:
Feed Zone: 160°C
Second Zone: 210°C
Third Zone: 235°C
Fourth Zone: 260°C
Fifth Zone: 285°C
Adapter Zone: 285°C
Die Zone: 285°C
Melt Temperature: 235 to 285°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

