

STARCOM S/2050 RAL 9003

Flexible Polyvinyl Chloride

Daloga srl

Message:

STARCOM S/2050 RAL 9003 is a Flexible Polyvinyl Chloride material. It is available in Europe for injection molding.

General Information			
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.43 to 1.47	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 30 sec)	83 to 87		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	11.7 to 14.3	MPa	ISO 527-2
Tensile Strain (Break)	250 to 310	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Ductile / Brittle Transition Temperature	-22.0 to -18.0	°C	ISO 458

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

