

SABIC® PPcompound 2550-4

Polypropylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® PPcompound 2550/4 is a mineral filled modified polypropylene. Typical material properties include good flow, high impact, good stiffness, low gloss and low CLTE. Typical application of this materials includes automotive exterior parts such as trims and bumpers with large unpainted areas. It can be used in painted and unpainted applications with UV stabilization added on demand.

SABIC® PPcompound 2550/4 is a designated automotive grade.

General Information			
Filler / Reinforcement	Mineral		
Additive	Impact Modifier		
Features	Good Flow		
	Good Stiffness		
	High Impact Resistance		
	Impact Modified		
	Low CLTE		
	Low Gloss		
	Paintable		
Uses	Automotive Applications		
	Automotive Bumper		
	Automotive Exterior Parts		
	Automotive Exterior Trim		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ISO 1133
Molding Shrinkage (24 hr)	0.90	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Injection Molded)	60		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/5/50
Yield, 3.20 mm, Injection Molded	16.0	MPa	
Break, 3.20 mm, Injection Molded	13.0	MPa	
Tensile Strain (Break, 3.20 mm, Injection Molded)	100	%	ISO 527-2/5/50
Flexural Modulus ¹ (Injection Molded)	1100	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C, Injection Molded)	No Break		ISO 179/1eA
Charpy Unnotched Impact Strength (-40°C, Injection Molded)	No Break		ISO 179/1eU
Notched Izod Impact Strength			ISO 180/4A
-20°C, Injection Molded	No Break		
0°C, Injection Molded	No Break		
23°C, Injection Molded	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
Vicat Softening Temperature	120	°C	ISO 306/A
CLTE - Flow			ASTM D696
-30 to 30°C	6.0E-5	cm/cm/°C	
23 to 80°C	1.0E-4	cm/cm/°C	
NOTE			

1. Method I (3 point load)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

