

Durethan® AKV 25 F30 000000

Polyamide 66

LANXESS GmbH

Message:

PA 66, 25 % glass fibers, injection molding, flame retardant

General Information				
UL YellowCard	E245249-100668706	E245249-101458614		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight			
Additive	Flame Retardant			
Features	Flame Retardant			
Processing Method	Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.60	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Across Flow : 290°C, 2.00 mm ¹	0.70	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.30	--	%	
Flow : 290°C, 2.00 mm ³	0.40	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	3.9	--	%	
Equilibrium, 23°C, 50% RH	1.2	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	10500	8000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	150	100	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.2	2.8	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	10000	7300	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	220	160	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	2.5	3.5	%	ISO 178/A
ISO Shortname	PA 66,GFHR,14-100,GF25; ISO 1043-PA GF FR(17)			ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	40	40	kJ/m ²	
23°C	50	50	kJ/m ²	

Notched Izod Impact Strength (23°C)	< 10	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	40	40	kJ/m ²	
23°C	45	45	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	> 240	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	238	--	°C	ISO 75-2/A
Vicat Softening Temperature	240	--	°C	ISO 306/B120
Melting Temperature ⁸	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	3.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	400	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.400 mm	V-0	--		
0.750 mm	V-0	--		
	V-0			
1.00 mm	5VA	--		
	V-0			
3.00 mm	5VA	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.400 mm	960	--	°C	
0.800 mm	960	--	°C	
1.50 mm	960	--	°C	
3.00 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.400 mm	875	--	°C	
0.800 mm	775	--	°C	
1.50 mm	775	--	°C	
3.00 mm	900	--	°C	
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	

Drying Time - Dry Air Dryer	2.0 to 6.0	hr
Processing (Melt) Temp	270 to 290	°C
Mold Temperature	80.0 to 100	°C

NOTE

1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

