

Formolene® L62009B

Linear Low Density Polyethylene

Formosa Plastics Corporation, U.S.A.

Message:

Formolene® L62009B is a general-purpose film grade linear low density made using gas-phase technology. The resin exhibits excellent toughness and strength when drawn down to thin gauges.
Formolene® L62009B meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR177.1520, covering safe use of polyolefin articles intended for direct food contact.

General Information			
Features	General Purpose		
	High Strength		
	Low Density		
	Ultra High Toughness		
Uses	Bags		
	General Purpose		
	Liners		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Coextrusion		
	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.919	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.95	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
Tensile Strength			ASTM D882
MD : Break	32.8	MPa	
TD : Break	24.0	MPa	
Tensile Elongation			ASTM D882
MD : Break	520	%	
TD : Break	780	%	
Dart Drop Impact	160	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	400	g	
TD	630	g	
Optical	Nominal Value	Unit	Test Method

Gloss (45°)	33		ASTM D523
Haze	21	%	ASTM D1003
Additional Information	Nominal Value		
Blow-up Ratio	2.5:1		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

