

# Chemical Resources PA6670GH

Polyamide 66  
Chemical Resources, Inc.

Message:

PA6670GH is a glass filled, heat stabilized, moisture resistant polyamide 66 resin suitable for injection molding.

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	Moisture Resistant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm <sup>3</sup>	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8270	MPa	ISO 527-2
Tensile Stress (Break)	180	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	261	°C	ISO 75-2/B
Melting Temperature	262	°C	ISO 11357-3

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

  
WECHAT