

Alcryn® 2170 BK

Melt Processable Rubber

Advanced Polymer Alloys

Message:

Alcryn® 2170 BK is a melt processable rubber (MPR) material. This product is available in North America, Europe or Asia Pacific.

Alcryn®The main features of 2170 BK are:

Comply with WEEE standard

ROHS certification

high liquidity

Good tear strength

chemical resistance

Typical application areas include:

Wire and cable

Automotive Industry

Hose

engineering/industrial accessories

Sealing applications

| General Information | | | |
|---|---------------------------------|-------------------|---------------------|
| Features | High Friction | | |
| | Good tear strength | | |
| | Good wear resistance | | |
| | High liquidity | | |
| | Good chemical resistance | | |
| Uses | Handle | | |
| | Cable sheath | | |
| | Wire sheath | | |
| | Washer | | |
| | Pipe | | |
| | Pipe fittings | | |
| | Seals | | |
| | Weather-resistant sealing strip | | |
| | Car interior parts | | |
| Agency Ratings | EU 2002/96/EC (WEEE) | | |
| RoHS Compliance | RoHS compliance | | |
| Appearance | Black | | |
| Forms | Particle | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.21 | g/cm ³ | ASTM D792, ISO 1183 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 1.90 mm, Compression Molded) | 69 | | ASTM D2240, ISO 868 |

| Elastomers | Nominal Value | Unit | Test Method |
|-----------------------------------|---------------|------|--------------------|
| Tensile Stress | | | |
| 100% strain | 3.00 | MPa | ASTM D412 |
| 100% strain, 1.90mm | 3.00 | MPa | ISO 37 |
| Tensile Strength | | | |
| Fracture, 1.90mm | 12.5 | MPa | ASTM D412 |
| Fracture, 1.90mm | 11.8 | MPa | ISO 37 |
| Tensile Elongation | | | |
| Fracture | 570 | % | ASTM D412 |
| Fracture, 1.90mm | 570 | % | ISO 37 |
| Tear Strength ¹ (24°C) | 57.0 | kN/m | ASTM D624 |
| Compression Set | | | |
| | | | ASTM D395, ISO 815 |
| 24°C, 22 hr | 19 | % | ASTM D395, ISO 815 |
| 100°C, 22 hr | 89 | % | ASTM D395, ISO 815 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -58.0 | °C | ASTM D746, ISO 812 |

Additional Information

The value listed as Specific Gravity, ASTM D792, was tested in accordance with ASTM D471. The value listed as Density, ISO 1183, was tested in accordance with ISO 2781. The value listed as Shore Hardness, ISO 868, was tested in accordance with ISO 48. Permanent Set (Tension), ASTM D412, Compression Molding, 1.9 mm: 15% 100% Modulus, ASTM D412, ISO 37, Physical Retention After 7 Days at 125°C, Compression Molding, 1.9 mm: 146% Tensile Strength, ASTM D412, ISO 37, DIN 53504, Physical Retention After 7 Days at 125°C, Compression Molding, 1.9 mm: 122% Elongation At Break, ASTM D412, ISO 37, Physical Retention After 7 Days at 125°C, Compression Molding, 1.9 mm: 96% Hardness, ISO 48, Physical Retention After 7 Days at 125°C, Shore A, Compression Molding, 1.9 mm: 69 Viscosity, ASTM D3835, 300 s-1 at 190°C, Compression Molding, 1.9 mm: 275 Pa*s Typical Processing Temperature, Compression Molding, 1.9 mm: 177° C Volume Change, ASTM D471, ISO 1817, After 7 days, 100°C, Water, Compression Molding, 1.9 mm: 19% Volume Change, After 7 days, ASTM D471, ISO 1817, 24°C, Fuel B, Compression Molding, 1.9 mm: 17% Volume Change, After 7 days, ASTM D471, ISO 1817, 100°C, ASTM #1 Oil, Compression Molding, 1.9 mm: -16% Volume Change, After 7 days, ASTM D471, ISO 1817, 100°C, IRM 903 Oil #3, Compression Molding, 1.9 mm: 6% Clash-Berg Stiffness Temperature, ASTM D1043, 10000 psi, Compression Molding, 1.9 mm: -38° C

NOTE

1. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT