

# Huafon JF-W-TL4060

Polyurethane

Huafon Group Co., Ltd.

## Message:

TOL Reduction Wet Process PU Resin for Micro Fibre Leather

### Characteristics

Mid soft type, acid and alkali resistance, hydrolysis resistance, good dyeing property, good elasticity, good film property, full of feeling, suit for TOL reduction technology.

### Applications

For microfiber non-woven fabric

General Information		
Features	Acid Resistant	
	Alkali Resistant	
	High Elasticity	
	Hydrolysis Resistant	
	Soft	
Uses	Fabrics	
	Nonwovens	
Additional Information	Nominal Value	Unit
Solvents	DMF	
Uncured Properties	Nominal Value	Unit
Solids Content	29 to 31	%
Viscosity (25°C)	100 to 160	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	5.00 to 6.00	MPa
Tensile Strength	> 30.0	MPa
Tensile Elongation at Break	> 400	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT