

HiFill® HDPE GF25 CC

High Density Polyethylene

Techmer Engineered Solutions

Message:

HiFill® HDPE GF25 CC is a High Density Polyethylene product filled with 25% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

Chemically Coupled

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	Chemically Coupled		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	0.030	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	76		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	48.3	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	160	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	129	°C	
1.8 MPa, Unannealed	121	°C	
CLTE - Flow	5.4E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	76.7	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	232 to 260	°C	

Middle Temperature	232 to 260	°C
Front Temperature	232 to 260	°C
Processing (Melt) Temp	218 to 246	°C
Mold Temperature	26.7 to 48.9	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	30 to 60	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT