

# Bionate® II 90A

Polycarbonate + TPU  
DSM Biomedical Inc.

Message:

Bionate® II 90A is a Polycarbonate + TPU (PC+TPU) product. It can be processed by extrusion or injection molding and is available in North America. Applications of Bionate® II 90A include medical/healthcare and food contact applications. Characteristics include:  
Good Mold Release  
Good Toughness  
High Strength  
Wear Resistant

General Information			
Features	Aromatic		
	Good Abrasion Resistance		
	Good Mold Release		
	Good Toughness		
	High Strength		
	Oxidation Resistant		
Uses	Medical/Healthcare Applications		
Agency Ratings	DMF Unspecified Rating		
	FDA Unspecified Rating		
Appearance	Clear Amber		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) <sup>1</sup>	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.83 to 2.7	%	ASTM D955
Water Absorption (Saturation)	0.72	%	ASTM D750
Average Molecular Weight	262000	Mw	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	92		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	59.4	MPa	ASTM D1708
Tensile Stress			ASTM D1708
50% Strain	9.36	MPa	
100% Strain	13.2	MPa	
300% Strain	44.9	MPa	

Tensile Elongation (Break)	390	%	ASTM D1708
Flexural Modulus - 1% Secant	45.1	MPa	ASTM D790
Flexural Strength (5.0% Strain)	2.16	MPa	ASTM D790
Coefficient of Friction (vs. Itself - Dynamic)	0.43		ASTM D1894
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Glass Transition Temperature	-2.00	°C	ASTM E1356
Vicat Softening Temperature	94.7	°C	ASTM D1525
Melting Temperature	177	°C	ASTM E1356
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.97		ASTM D150
<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>	
Processing (Melt) Temp	191 to 218	°C	
<b>Extrusion</b>	<b>Nominal Value</b>	<b>Unit</b>	
Melt Temperature	177 to 210	°C	
<b>NOTE</b>			
1.	224°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT