

CP PRYME® Nylon 66 NN300STHSL NAT

Polyamide 66
Chase Plastics Services Inc.

Message:
Reprocessed Nylon 6/6, Super Tough, Heat Stabilized, Lubricated, Natural

General Information			
Additive	Heat Stabilizer		
	Lubricant		
Features	Heat Stabilized		
	Lubricated		
	Ultra High Toughness		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Ash Content	0.80	%	ASTM D789
Moisture Content	< 0.25	%	ASTM D789
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	42.0	MPa	ASTM D638
Tensile Elongation (Break)	45	%	ASTM D638
Flexural Modulus	1720	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	188	°C	
1.8 MPa, Unannealed	57.0	°C	
Melting Temperature	254	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT