

# Electrafil® HDPE C BK

High Density Polyethylene

Techmer Engineered Solutions

## Message:

Electrafil® HDPE C BK is a High Density Polyethylene product. It can be processed by injection molding and is available in North America.

General Information			
UL File Number	E157318		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.953	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/1.05 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	3.0	%	ASTM D955
Water Absorption (24 hr)	0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	45		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	31.0	MPa	ASTM D638
Tensile Elongation (Break)	600	%	ASTM D638
Flexural Modulus	1210	MPa	ASTM D790
Flexural Strength	41.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	60.0	°C	ASTM D648
CLTE - Flow	1.4E-4	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT